C10100

2.7. Cu-OFE



ENGINEERING COPPER SOLUTIONS

Alloy Designation	
EN	Cu-OFE
DIN CEN/TS 13604	CW009A
UNS	C10100

Chemical Composition Weight percentage	n (Balance)	
Cu	≥ 99.99	%

Characteristics

Cu-OFE is a high-purity, oxygen-free copper, that does not contain elements that can vaporise in a vacuum environment. It is very thermally and electrically conductive and it also performs extremely well during hot and cold forming. Cu-OFE is corrosion-resistant, especially against atmospheric influences and water, and is also insensitive to stress corrosion cracking.

Main Applications

Cu-OFE is a popular material in electrical engineering, vacuum engineering and the production of high-frequency cables.

Mechanical Properties (EN 1652)						
Temper	Tensile Strength	Yield Strength Minimum	Elongation Minimum	Hardness		i ding 0°
	Rm	Rp _{0.2}	A _{50mm}	HV *	gw rel. Bendin	bw g Radius R/T
	MPa	MPa	%	HV	Strip Thickn	ess ≤ 0.50mm
R220	220260	≤ 140 *	33	40 65	0	0
R240	240300	180	8	65 95	0	0
R290	290360	250	4	90110	0	0
R360	≥ 360	320	2	≥ 110	0	0.5

* only for information

Physical	Properties	

Physical Properties Typical values in annealed temper at 20 °C			
Density		8.93	g/cm³
Thermal expansion coefficient	20 300 °C	17.7	10 ⁻⁶ /K
Specific heat capacity		0.39	J/(g·K)
Thermal conductivity		394	W/(m·K)
Electrical conductivity	MS/m	58.6	MS/m
Electrical conductivity	IACS	101	%
Thermal coefficient of electrical resistance	(0 100 °C)	3.81	10 ⁻³ /K
Modulus of elasticity	GPa	130	GPa

Fabrication Properties *	
Cold Forming Properties	Excellent
Machinability (Rating 20)	Less suitable
Electroplating Properties	Excellent
Hot Tinning Properties	Excellent
Soft Soldering, Brazing	Excellent
Resistance Welding	Less suitable
Gas Shielded Arc Welding	Excellent
Laser Welding	Fair

* For more details call our technical service

Due to continuous improvements within our production process, the details given in our brochure cannot be guaranteed. We reserve the right to update or change our products without prior notice. We recommend that you seek confirmation of our product details / specifications before committing to specific alloys.