C51000

4.6. CuSn5



Alloy Designation	
EN	CuSn5
DIN CEN/TS 13388	CW451K
UNS	C51000

Chemical Composition Weight percentage	ı (Balance)	
Cu	Rest	%
Sn	5	%
P	0.1	%

Characteristics

CuSn5 provides an excellent combination of strength, excellent formability and hardness. It has a good electrical conductivity and corrosion resistance. Soldering and brazing properties are excellent.

Main Applications

Stamped parts, Connectors, Contact springs, Spring elements, Ultra high strength spring elements, Membranes, Switch elements, Fixed contacts.

Mechanical Properties (EN 1652)							
Temper	Tensile Strength	Yield Strength Standard	Yield Strength Bending optimized	Elongation Bending optimized (min.)	Hardness *	optimize	oding ed quality 10°
* only information	Rm	Rp _{0.2}	Rp _{0.2}	A _{50mm}		gw rel. Bendin	bw g Radius R/T
	МРа	MPa	MPa	%	HV	Strip Thickne	ess ≤ 0.50mm
R310	310 390	≤ 250 *			70105	0	0
R400	400 500	≥ 340		17	120 160	0	0
R490	490 580	≥ 450	≥ 440	19	160 190	0	0
R550	550 640	≥ 500	≥ 480	13	180 210	0	0.5
R630	630 720	≥ 570	≥ 560	7	200 230	0	1
R690	≥ 690	≥ 630	≥ 600	4	≥ 220	2	3

Physical Properties Typical values in annealed temper at 20 °C				
Density		8.94	g/cm³	
Thermal expansion coefficient	20 300 °C	17.8	10 ⁻⁶ /K	
Specific heat capacity		0.38	J/(g·K)	
Thermal conductivity		90	W/(m·K)	
Electrical conductivity	MS/m	10	MS/m	
Electrical conductivity	IACS	17	%	
Thermal coefficient of electrical resistance	(0 100 °C)	0.1	10 ⁻³ /K	
Modulus of elasticity	GPa	120	GPa	

Excellent
Less suitable
Excellent
Excellent
Excellent
Good
Good
Good

^{*}For more details call our technical service

Due to continuous improvements within our production process, the details given in our brochure cannot be guaranteed. We reserve the right to update or change our products without prior notice. We recommend that you seek confirmation of our product details / specifications before committing to specific alloys.