

Alloy Designation	
EN	CuNi10Fe1Mn
DIN CEN/TS 13388	CW352H
UNS	C70620

Chemical Composition (Balance)		
Weight percentage		
Cu	Rest	%
Ni	9 ... 11	%
Fe	1 ... 2	%
Mn	0.5 ... 1	%

Mechanical Properties						
Temper	Tensile Strength Rm	Yield Strength Minimum Rp0.2	Elongation Minimum A50mm	Hardness HV *	Bending 90°	
					gw rel. Bending Radius R/T	bw
	MPa	MPa	%	HV	Strip Thickness ≤ 0.50mm	
R300	≥ 300	100 *	20	≥ 70	0	0
R320	≥ 320	180 *	12	≥ 100	0	0
R420	420 .. 510	370 *	3	≥ 120	0	0.5
R520	520 .. 610	480 *	2	≥ 150	1	2
R620	≥ 620	590 *	-	≥ 170	-	-

* only for information

Physical Properties			
Typical values in annealed temper at 20 °C			
Density		8.89	g/cm ³
Thermal expansion coefficient	20 .. 300 °C	19.0	10 ⁻⁶ /K
Specific heat capacity		0.38	J/(g·K)
Thermal conductivity		50.2	W/(m·K)
Electrical conductivity	MS/m	5	MS/m
Electrical conductivity	IACS	9	%
Thermal coefficient of electrical resistance	(0 .. 100 °C)	7	10 ⁻³ /K
Modulus of elasticity	GPa	130	GPa

Fabrication Properties *	
Cold Forming Properties	Excellent
Machinability (Rating 20)	Good
Electroplating Properties	Good
Hot Tinning Properties	-
Soft Soldering, Brazing	Excellent
Resistance Welding	Excellent
Gas Shielded Arc Welding	Good
Laser Welding	Excellent

* For more details call our technical service

Characteristics

For many decades, copper-nickel alloy **CuNi10Fe1Mn** has extensively been used as a piping material for seawater systems in shipbuilding, offshore, and desalination industries. Attractive characteristics of this alloy combine excellent resistance to uniform corrosion, remarkable resistance to localised corrosion in chlorinated seawater, and higher erosion resistance than other copper alloys and steel. Furthermore, **CuNi10Fe1Mn** is resistant to biofouling providing various economic benefit.

Main Applications

Cladding for corrosion protection of steel structures, Sheathing on offshore structures, Piping systems, pipes, fittings, flanges, desalination plant, offshore wind structures, shipbuilding.