

Alloy Designation

EN	Cu-OFE
DIN CEN/TS 13604	CW009A
UNS	C10100

Chemical Composition (Balance)

Weight percentage

Cu	≥ 99.99	%
----	---------	---

Characteristics

**Cu-OFE** is a high-purity, oxygen-free copper, that does not contain elements that can vaporise in a vacuum environment. It is very thermally and electrically conductive and it also performs extremely well during hot and cold forming. Cu-OFE is corrosion-resistant, especially against atmospheric influences and water, and is also insensitive to stress corrosion cracking.

Main Applications

**Cu-OFE** is a popular material in electrical engineering, vacuum engineering and the production of high-frequency cables.

Mechanical Properties (EN 1652)

Temper	Tensile Strength Rm	Yield Strength Minimum Rp0.2	Elongation Minimum A50mm	Hardness HV *	Bending 90°	
	MPa	MPa	%	HV	gw rel. Bending Radius R/T	bw
	MPa	MPa	%	HV	Strip Thickness ≤ 0.50mm	
R220	220 .. 260	≤ 140 *	33	40 .. 65	0	0
R240	240 .. 300	180	8	65 .. 95	0	0
R290	290 .. 360	250	4	90 .. 110	0	0
R360	≥ 360	320	2	≥ 110	0	0.5

\* only for information

Physical Properties

Typical values in annealed temper at 20 °C

Density		8.93	g/cm <sup>3</sup>
Thermal expansion coefficient	20 .. 300 °C	17.7	10 <sup>-6</sup> /K
Specific heat capacity		0.39	J/(g·K)
Thermal conductivity		394	W/(m·K)
Electrical conductivity	MS/m	58.6	MS/m
Electrical conductivity	IACS	101	%
Thermal coefficient of electrical resistance	(0 .. 100 °C)	3.81	10 <sup>-3</sup> /K
Modulus of elasticity	GPa	130	GPa

Fabrication Properties \*

Cold Forming Properties	Excellent
Machinability (Rating 20)	Less suitable
Electroplating Properties	Excellent
Hot Tinning Properties	Excellent
Soft Soldering, Brazing	Excellent
Resistance Welding	Less suitable
Gas Shielded Arc Welding	Excellent
Laser Welding	Fair

\* For more details call our technical service

Due to continuous improvements within our production process, the details given in our brochure cannot be guaranteed. We reserve the right to update or change our products without prior notice. We recommend that you seek confirmation of our product details / specifications before committing to specific alloys.