

Alloy Designation	STOL® 78
EN	CuMgP
DIN CEN/TS 13388	
UNS	C18665

Characteristics

STOL® 78 is a high Magnesium (Mg) alloyed material with excellent formability at medium strength and good conductivity. Typical applications are automotive, electrical and electronic connectors, relays, current carrying springs and junction boxes.

Main Applications

Automotive: Switches and Relays, Contacts, Connectors, Terminals.

Electrical: Switches and Relays, Contacts, Connectors, Terminals, Components for the electrical industry, Stamped parts, Semiconductor Components.

Mechanical Properties (EN 1652)

Temper	Tensile Strength	Yield Strength Minimum	Elongation Minimum	Hardness	Bending 90°	
	Rm	Rp0.2	A50mm	HV *	gw rel. Bending Radius R/T	bw
	MPa	MPa	%	HV	Strip Thickness ≤ 0.50mm	
R380	380 .. 460	330	14	115 .. 145	0	0
R460	460 .. 520	410	10	140 .. 165	0.5	1
R520	520 .. 570	460	8	160 .. 180	1	2.5
R570	570 .. 620	500	6	175 .. 195	2.5	5
R620 **	≥ 620	550	3	≥ 190	3	6

*only for information / ** Thickness max. 0.50 mm

Physical Properties

Typical values in annealed temper at 20 °C

Density		8.81	g/cm³
Thermal expansion coefficient	20 .. 300 °C	17.3	10 ⁻⁶ /K
Specific heat capacity		0.32	J/(g·K)
Thermal conductivity		270	W/(m·K)
Electrical conductivity	MS/m	36	MS/m
Electrical conductivity	IACS	62	%
Thermal coefficient of electrical resistance	(0 .. 100 °C)	2.5	10 ⁻³ /K
Modulus of elasticity	GPa	130	GPa

Fabrication Properties *

Cold Forming Properties	Excellent
Machinability (Rating 20)	Less suitable
Electroplating Properties	Excellent
Hot Tinning Properties	Excellent
Soft Soldering, Brazing	Excellent
Resistance Welding	Less suitable
Gas Shielded Arc Welding	Excellent
Laser Welding	Fair

* For more details call our technical service