

Alloy Designation	STOL [®] 80
EN	CuSn0,2
DIN CEN/TS 13388	
UNS	C14410

Characteristics

STOL[®] 80 is a low Tin (Sn) special alloy that combines low cost with highest conductivity. The total cost for finish products are often equal to brass due to excellent conditions for stamping scrap.

Typical applications are male connectors and fuse boxes.

Chemical Composition (Balance)		
Weight percentage		
Cu	Rest	%
Sn	0.2	%
P	0.01	%

Main Applications

Automotive: Switches and Relays, Contacts, Connectors, Terminals.

Electrical: Switches and Relays, Contacts, Connectors, Terminals, Components for the electrical industry, Stamped parts, Semiconductor Components.

Mechanical Properties (EN 1652)						
Temper	Tensile Strength	Yield Strength Minimum	Elongation Minimum	Hardness	Bending 90°	
	Rm	Rp0.2	A50mm	HV *	gw rel. Bending Radius	bw R/T
	MPa	MPa	%	HV	Strip Thickness ≤ 0.50mm	
R250	≥ 250	≤ 140	20	60 .. 80	0	0
R300	300 .. 370	270	10	80 .. 100	0	0
R360	360 .. 430	310	7	110 .. 130	0	0
R420	420 .. 490	370	5	120 .. 150	1	1
R460	≥ 460	410	4	≥ 135	1	1.5

*only for information

Physical Properties			
Typical values in annealed temper at 20 °C			
Density		8.94	g/cm ³
Thermal expansion coefficient	20 .. 300 °C	17.3	10 ⁻⁶ /K
Specific heat capacity		0.385	J/(g·K)
Thermal conductivity		330	W/(m·K)
Electrical conductivity	MS/m	44	MS/m
Electrical conductivity	IACS	76	%
Thermal coefficient of electrical resistance	(0 .. 100 °C)	3.3	10 ⁻³ /K
Modulus of elasticity	GPa	120	GPa

Fabrication Properties *	
Cold Forming Properties	Excellent
Machinability (Rating 20)	Fair
Electroplating Properties	Excellent
Hot Tinning Properties	Excellent
Soft Soldering, Brazing	Excellent
Resistance Welding	Fair
Gas Shielded Arc Welding	Excellent
Laser Welding	Good

* For more details call our technical service

Due to continuous improvements within our production process, the details given in our brochure cannot be guaranteed. We reserve the right to update or change our products without prior notice. We recommend that you seek confirmation of our product details / specifications before committing to specific alloys.